



HB42[®] All-in-One | SEALANT & ADHESIVE

GEV EC1 Plus Approved

28/6/18 - Vs.1

TECHNICAL DATA SHEET

HB42 SEALANT & ADHESIVE / White, Black, Grey & Brown / 290ml cartridge

Sealant & Adhesive
Interior & Exterior
Works in wet
Flexible (Non shrinking)
Durable
Can be over-painted
Solvent free
Suitable as mirror adhesive
Bonds to almost anything (incl. lead)
Odourless
EC1 plus rated, very low VOC's.
Food safe

Conforms to EN 15651-1 & EN 15661-4

Conforms to INS PI No: 1806068 f or materials intended to come into contact with food. GEV Approved no: 8835/13.11.12: EC1Plus Classification for very low emissions
Hilton Banks Ltd: GEV Member OM-088

Uses:

Sealing joints around sanitary fixtures
Sealing joints around windows & doors (can be over-painted)
Weatherproofing joints
For use in glazing systems
Fixing skirting, panels, windows, thresholds, insulation materials
Fixing mirrors
Seals & bonds glass
Bonds & seals wood, stainless steel, aluminium, porcelain, UPVC, coated metal, polystyrene
May be used safely in food preparation areas

Application:

Ensure surfaces are clean & dust free. Cut the cartridge seal and screw on the nozzle, having cut to required size. Using a skeleton gun, apply sealant into the gap or joint to provide a good solid fill. If



HB42[®] All-in-One | SEALANT & ADHESIVE

GEV EC1 Plus Approved

required place masking tape along the edges, removing within 10 minutes of application. Use a sealant finishing tool or a stick wetted with soapy water to achieve smooth finish. For bonding applications, apply in vertical lines at a distance of 30cm. Support the application for 24 hours until full curing occurs. If painting, use a water-based paint.

Health & Safety

Contains Bis – (1.2.2.6.6-pentamethyl-4-piperidyl) sebacate,
N-(3-(trimethoxysilyl)propyl)ethylenediamine, 3-(2-aminoethylamino) propyltrimethoxysilane.
May produce an allergic reaction. See safety data sheet, available on www.hiltonbanks.com

Limitations

HB42 Sealant & Adhesive is not recommended for use on PE, PP, Teflon, wax, neoprene and bituminous surfaces. Not suitable for aquaria. Not paintable with alkyd resin paint. Not suitable for sealing insulation glass or in contact with PVB foil or coat glass. On porous surfaces such as concrete, a primer is recommended. It is the users' responsibility to determine suitability, tests prior to application are recommended. Store between +5 & +25 degrees centigrade in cool dry conditions.

Liability

The information given is the result of tests and experience and is believed to be accurate & reliable. As Hilton Banks Ltd cannot know all the uses that HB42 Sealant & Adhesive may be put to or control how it is applied, it is the responsibility of the user to determine suitability of use.

TECHNICAL DATA

COLOURS

Density	g/ml	1,48
Skin forming time 23 °C/55%RH	min	40
Max movement allowed ISO 9040	%	25
Temperature resistance after curing	°C	-40- +90
Shrinkage		nil
Curing (24 hours) 23 °C/55%RH	mm	2-3
Mechanical properties		
2mm film		
Hardness, Shore A DIN ISO 868		40
Modulus, 100% ISO 8339	N/MM ²	0.80
Elongation at break ISO 8339	%	230
Modulus At Break ISO 8339	N/MM ²	1.10



HB42[®] All-in-One | SEALANT & ADHESIVE

GEV EC1 Plus Approved

Hilton Banks Ltd, 74 Oldfield Road, Hampton, Middx, TW12 2HR
Tel: 020 8979 8284 www.hiltonbanks.com

